

# CBGM-SHOTCRETE-AbrasionResistant Grout

High durability shotcrete with superior wear resistance.

## Key Features

- Excellent abrasion resistance
- High compressive strength  $\geq 100$  MPa
- Durable and volume stable
- Long service life

## Technical Parameters

Parameter	Value
Compressive Strength (28 d)	$\geq 100$ MPa
Flexural Strength	$\geq 18$ MPa
Abrasion Resistance	Excellent
Chloride Diffusion	$\leq 2.0 \times 10^{-14}$ m <sup>2</sup> /s

## Applications

- Mining tunnels and shafts
- Hydraulic structures and dams
- Industrial floors
- Tunnel linings

## Mixing & Application Instructions

1. Mix with clean water ( $12 \pm 1\%$ ).
  2. Stir mechanically 3–5 min.
  3. Spray with shotcrete equipment.
  4. Cure 7 days moist.
- Do not apply below 0 °C.

## Packaging & Storage

25 kg/bag, 12 months sealed

## Disclaimer

All data is based on tests and experience. No guarantee. Users must verify suitability.

[www.zrete.com](http://www.zrete.com) | [info@wcrete.com](mailto:info@wcrete.com) | Tel: +86-15373872353