

CBGM-SHOTCRETE-NoShrink Grout

Volume-stable shotcrete for reliable repairs.

Key Features

- Non shrinkage and volume stability
- High bonding strength
- Durable under sustained load
- Low rebound spraying

Technical Parameters

Parameter	Value
Compressive Strength (28 d)	≥90 MPa
Flexural Strength	≥15 MPa
Volume Stability	Non Shrinkage
Chloride Diffusion	≤2.0×10 ⁻¹⁴ m²/s

Applications

- Bridge and tunnel repair
- Industrial reinforcement
- Water retaining structures
- Infrastructure maintenance

Mixing & Application Instructions

1. Mix with clean water (12 ± 1%).
 2. Stir mechanically 3–5 min.
 3. Spray with shotcrete equipment.
 4. Cure 7 days moist.
- Do not apply below 0 °C.

Packaging & Storage

25 kg/bag, 12 months sealed

Disclaimer

All data is based on tests and experience. No guarantee. Users must verify suitability.

www.zrete.com | info@wcrete.com | Tel: +86-15373872353