

CBGM-SHOTCRETE-EarlyStrength Grout

Rapid setting shotcrete for early structural support.

Key Features

- ≥ 20 MPa compressive in 24h
- Fast setting
- Low rebound
- Cold climate suitable

Technical Parameters

Parameter	Value
Compressive (1d)	≥ 20 MPa
Compressive (28d)	≥ 80 MPa
Flexural	≥ 12 MPa

Applications

- Mining support
- Tunnel excavation
- Emergency repair
- Cold climates

Mixing & Application Instructions

1. Mix with clean water ($12 \pm 1\%$).
 2. Stir mechanically 3–5 min.
 3. Spray with shotcrete equipment.
 4. Cure 7 days moist.
- Do not apply below 0 °C.

Packaging & Storage

25 kg/bag, 12 months sealed

Disclaimer

All data is based on tests and experience. No guarantee. Users must verify suitability.

www.zrete.com | info@wcrete.com | Tel: +86-15373872353